



3250 Linebaugh Rd.  
 Xenia, OH 45385  
 Telephone (800) 762-0040  
 FAX (937) 879-8425

**CEMENT  
MILL  
TEST**

**Cement Identified as:** **Masonry Cement, Type S** **Date:** **09/28/20**  
**Production Dates:** **August, 2020**

PHYSICAL REQUIREMENTS	SPECIFICATIONS	ASTM C 91 Type S	RESULTS
(ASTM C 430) 45-um sieve, % retained	Maximum	24	7
(ASTM C 151) Autoclave Expansion, %	Maximum	1.0	0.12
(ASTM C 266) Time of Setting (Gillmore)			
Initial Set, minutes	Minimum	90	255
Final Set, minutes	Maximum	1000	335
(ASTM C 185) Air Content, %	Range	8-19	20
(ASTM C 1506) Water Retention	Minimum	70	82
(ASTM C 109) Compressive Strength, psi (Mpa)			
7 Day	Minimum	1300 ( 9.0 )	2540 ( 17.5 )
28 Day	Minimum	2100 (14.5 )	2780 ( 19.2 )

'We hereby certify that this cement conforms to all of the standard requirements for masonry cement in the above specification for the type specified.

By: *Rusty Strader*

Physical Testing completed by: DG, MS  
 Chemical Testing completed by: TA, NC, JDC, NM

Rusty Strader  
 Quality Control Manager  
 Fairborn Cement Company