



3250 Linebaugh Rd.  
 Xenia, OH 45385  
 Telephone (800) 762-0040  
 FAX (937) 879-8425

**CEMENT  
MILL  
TEST**

**Cement Identified as:** Type I, Type II **Date:** 08/02/21

**Production Period:** June, 2021 **Silos:** 2, 6

STANDARD CHEMICAL REQUIREMENTS (ASTM C 114)	SPECIFICATIONS	ASTM C 150		AASHTO	RESULTS
		TYPE I	TYPE II (MH)	M85 Type I	
Silicon Dioxide (SiO <sub>2</sub> ), %		-----	-----	-----	<b>19.1</b>
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	Maximum	-----	6.0	-----	<b>4.5</b>
Ferric Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	Maximum	-----	6.0	-----	<b>3.0</b>
Calcium Oxide (CaO), %		-----	-----	-----	<b>61.7</b>
Magnesium Oxide (MgO), %	Maximum	6.0	6.0	6.0	<b>4.8</b>
Sulfur Trioxide (SO <sub>3</sub> ), % <sup>A</sup>	Maximum	3.0	3.0	3.0	<b>3.3</b>
Loss on Ignition (LOI), %	Maximum	3.5	3.5	3.5	<b>2.6</b>
Insoluble Residue, %	Maximum	1.50	1.50	1.5	<b>0.62</b>
Alkalies (Na <sub>2</sub> O equivalent), %		-----	-----	-----	<b>0.88</b>
Tricalcium Silicate (C <sub>3</sub> S), Potential %		-----	-----	-----	<b>60</b>
Dicalcium Silicate (C <sub>2</sub> S), Potential %		-----	-----	-----	<b>7</b>
Tricalcium Aluminate (C <sub>3</sub> A), Potential %	Maximum	-----	8	-----	<b>7</b>
Tetracalcium Aluminoferrite (C <sub>4</sub> AF), Potential %		-----	-----	-----	<b>9</b>
C <sub>3</sub> S + 4.75C <sub>3</sub> A	Maximum		100		<b>91</b>
CO <sub>2</sub> , %					<b>1.6</b>
Limestone, %	Maximum	5.0	5.0		<b>3.8</b>
CaCO <sub>3</sub> in Limestone, %	Minimum	70	70		<b>97</b>
<b>PHYSICAL REQUIREMENTS</b>					
(ASTM C 204) Blaine Fineness, m <sup>2</sup> /kg	Range	260 Min.	260 - 430	260 Min.	<b>407</b>
(ASTM C 191) Time of Setting (Vicat)					
Initial Set, minutes	Minimum	45	45	45	<b>95</b>
Final Set, minutes	Maximum	375	375	375	<b>207</b>
(ASTM C 185) Air Content, %	Maximum	12	12	12	<b>7</b>
(ASTM C 151) Autoclave Expansion, %	Maximum	0.80	0.80	0.80	<b>0.20</b>
(ASTM C 1038) Expansion in Water, %	Maximum	0.02	0.02	0.02	<b>0.010</b>
(ASTM C 187) Normal Consistency, %		-----	-----	-----	<b>26.3</b>
Heat of Hydration (ASTM C 1702)					
3 day, cal/g	Most Recent Value				<b>82</b>
(ASTM C 109) Compressive Strength, psi (Mpa)				-----	
1 Day		-----	-----	-----	<b>2754 ( 19.0 )</b>
3 Day	Minimum	1740 ( 12.0 )	1450 ( 10.0 )	1740 (12.0)	<b>4311 ( 29.7 )</b>
7 Day	Minimum	2760 ( 19.0 )	2470 ( 17.0 )	2760 (19.0)	<b>5087 ( 35.1 )</b>
28 Day	Minimum	4060 ( 28.0 )	4060 ( 28.0 )	4060 (28.0)	<b>6079 ( 41.9 )</b>

<sup>A</sup> Per ASTM C150 Table 1 footnote D

We hereby certify that this cement conforms to all of the standard requirements for portland cement in the above specification for the type specified.

By: Rusty Strader

Physical Testing completed by: DG, MS  
 Chemical Testing completed by: TA, NC, KL, NM

Rusty Strader  
 Quality Control Manager  
 Fairborn Cement Company



3250 Linebaugh Rd.  
 Xenia, OH 45385  
 Telephone (800) 762-0040  
 FAX (937) 879-8425

**CEMENT  
MILL  
TEST**

**Cement Identified as:** Type I, Type II **Date:** 08/02/21  
**Production Period:** June, 2021 **Silos:** 2, 6

**Additional Data**

Type	Inorganic Processing Addition Data	
	Baghouse Dust	Limestone
Amount (%)	0.8	3.8
SiO2 (%)	12.0	2.6
Al2O3 (%)	4.1	1.1
Fe2O3 (%)	1.6	0.6
CaO (%)	43.2	50.4
SO3 (%)	0.7	0.4

Base cement Phase Composition

C3S (%)	55
C2S (%)	12
C3A (%)	7
C4AF (%)	9

We hereby certify that this cement conforms to all of the standard requirements for portland cement in the above specification for the type specified.

By: Rusty Strader

Rusty Strader  
 Quality Control Manager  
 Fairborn Cement Company